

# SPECIALTY RESIN



## PROBLEND™ LOW TOC THROW HIGH CAPACITY MIXED BED RESIN

**ProBlend™ Low TOC Throw High Capacity (P/N ER30005)** is a high grade mixed bed made to attain very low leachable TOC levels. The product is fully tested to ensure its ability to achieve 18 megohm resistivity. Each batch is also tested to ensure its ability to rinse to below 25 ppb of leachable TOC in less than 25 bed volumes from start up and to below 10 ppb in less than 50 bed volumes.\*

### FEATURES

- Complies with USDA & FDA regulations (paragraph 21 CFR173.25) for potable water applications \*
- Designed to provide ultra-high purity water
- Highest operating capacity
- Low effluent TOC values
- Superior thermal and physical stability
- Excellent regenerable capacities for inorganic and organic ions

\* For potable water applications, the resin must be properly pre-treated, usually by multiple exhaustion and regeneration cycles, to insure compliance with extractable levels.

### Suggested Operating Conditions

Maximum Temperature	
Non-regenerable **	175°F (80°C)
Regenerable	140°F (60°C)
Operating Flow Rate (Typical)	2 to 10 gpm/cu.ft.
Backwash Rate (See graph on next page)	
Pressure Drop (See graph on next page)	
Metals Content (Typical ppm dry weight)	
Iron (Fe)	100 ppm maximum
Copper (Cu)	50 ppm maximum
Lead (Pb)	50 ppm maximum
Percent Conversions to Ionic Form	
Cation H	99% minimum
Anion OH	90% minimum ***
Cl + SO <sub>4</sub>	10% maximum
CO <sub>3</sub>	*** (See note below)

### Limitations

Extended exposure to strong oxidizers (such as chlorine, hydrogen peroxide, and concentrated nitric acid) degrade the structural backbone of the resin and should be avoided.

\* Influent greater than 1 megohm.

\*\* 6 month typical resin life at 175°F.

\*\*\* Hydroxides measured in anion component prior to mixing. The CO<sub>3</sub> level measured immediately after production is held to the same specifications as the SO<sub>4</sub>. Actual CO<sub>3</sub> levels may change during storage and shipment due to adsorption of CO<sub>2</sub> from the atmosphere. We recommend keeping all containers sealed closed until use. For longer storage times, gas barrier packaging (mylar) is suggested. Contact your SWT for more information.

**CAUTION: DO NOT MIX ION EXCHANGE RESINS WITH STRONG OXIDIZING AGENTS.** Nitric acid and other strong oxidizing agents can cause explosive reactions when mixed with organic materials such as ion exchange resins.

Note: These suggestions and data are based on information we believe to be reliable. However, we do not make any guarantee or warranty. We caution against using these products in any unsafe manner or in violation of any patents. Further, we assume no liability for the consequences of any such actions.

### Physical Properties

#### Functional Structure


Cation	RSO <sub>3</sub> <sup>-</sup> H <sup>+</sup> (Hydrogen form gelular sulfonated polystyrene copolymer)
Anion	R <sub>4</sub> N <sup>+</sup> OH <sup>-</sup> (Hydroxyl form Type 1 porous gel strong base alkyl quaternary ammonium polystyrene copolymer)

Physical Form	Spherical beads
Screen Size Distribution	16 to 45 nominal
+16 mesh (U.S. Std.)	2% maximum
-45 mesh (U.S. Std.)	2% maximum
pH Range	0 to 14
Moisture Content (as shipped)	60% maximum
Approximate Shipping Weight	43 lbs/cu.ft.
Volume Ratio (as shipped)	
Anion/Cation	60/40
Total Capacity	
Cation (Na <sup>+</sup> form)	1.95 meq/mL minimum
Anion (Cl <sup>-</sup> form)	1.40 meq/mL minimum


# SPECIALTY RESIN



## PROBLEND™ LOW TOC THROW HIGH CAPACITY MIXED BED RESIN



**PRESSURE DROP** — The graph above shows the expected pressure loss per foot of bed depth as a function of flow rate at various temperatures.



**BACKWASH** — The backwash step is used to separate the components prior to regeneration and to remove particles. The separation is optimized at a bed expansion of 50 to 75 percent.

### ProBlend™ High Capacity Resins Comparison Table

Specifications	Nuclear Grade (P/N ER30008)	Semi-Conductor (P/N ER30004)	Low TOC Throw (P/N ER30005)	Ultra Low TOC Throw (P/N ER30009)
Resistivity in polishing 18 megohm water @ 60 bed volumes per hour (megohm)	> 15**	> 18	> 18	> 18
Leachable TOC @ 25 bed volumes from start up (ppb as C) *	No Spec	No Spec	< 25	< 25
Leachable TOC @ 50 bed volumes from start up (ppb as C) *	No Spec	< 50	< 10	< 5
Leachable TOC @ 100 bed volumes from start up (ppb as C) *	No Spec	No Spec	No Spec	1

\* Leachable TOC measured at 0.5 bed volumes per minute at 175°F.

\*\* Influent greater than 1 megohm.